

# ACEROS CORRUGADOS



**MARCELIANO MARTÍN**  
ACERO EN MOVIMIENTO



# ACERO CORRUGADO

## Según UNE 36740:98

Diámetro (mm)	Kg./m	B 400 SD		B 500 S	
		Altura mínima de corruga (a) (mm) (1)	Separación de corrugas (c) (mm) (2)	Altura mínima de corruga (a) (mm) (1)	Separación de corrugas (c) (mm) (2)
6	0,222	0,25	4,98	0,28	4,27
8	0,395	0,34	6,65	0,37	5,69
10	0,617	0,38	7,40	0,47	7,11
12	0,888	0,69	7,75	0,65	7,54
16	1,578	0,84	9,41	0,87	10,05
20	2,470	1,05	11,76	1,08	12,56
25	3,850	1,39	15,15	1,37	15,31
32	6,310	1,77	19,39	1,75	19,60
40	9,860	2,22	24,24	2,19	24,50

